บทคัดย่อ

การศึกษาสมบัติทางกายภาพของน้ำยางโปรตีนต่ำเพื่อดูความเป็นไปได้ในการนำน้ำ ยางโปรตีนไปใช้ทำผลิตภัณฑ์ยางฟิล์มที่ปราศจากการแพ้ กระบวนการกำจัดโปรตีนออกจาก ยางธรรมชาติทำได้โดยการบ่มน้ำยางขันแอมโมเนียสูงด้วยยูเรีย 0.1 wt% และสารสบู่เป็นเวลา ชั่วโมง ที่อุณหภูมิห้อง เปรียบเทียบกับการกำจัดโปรตีนแบบเดิมที่บ่มด้วยโปรทิโอไลติก เอนไซม์ 0.04 wt% และสารสบู่เป็นเวลา 24 ชั่วโมง ที่อุณหภูมิ 38°C จากการทดสอบปริมาณ ในโตรเจนของน้ำยางหลังกำจัดโปรตีนด้วยยูเรียลดลงเหลือ 0.06 wt% จากเดิมน้ำยางขัน 0.45 wt% ในสภาวะที่ทำการทดลองนี้ นอกจากปริมาณโปรตีนที่ละลายน้ำของน้ำยางหลังการบ่มด้วย ยูเรียจะลดลงเหลือ 15 μg/g จากเดิมน้ำยางขัน 42,455 μg/g โดยการลดลงของปริมาณโปรตีน นี้สามารถยืนยันผลโดยดูจากโครงสร้างทางเคมีด้วยเทคนิคอินฟราเรดสเปกโตรสโคปี เสนอว่า กระบวนการกำจัดโปรตีนด้วยยูเรียดังกล่าวมีประสิทธิภาพเทียบเท่าแบบเดิม ต่อมาได้ทำการทดสอบสมบัติทางกายภาพของน้ำยางดังกล่าว พบว่าปริมาณ ประหยัดกว่า ของแข็งทั้งหมดและปริมาณเนื้อยางแห้งของยางโปรตีนต่ำบ่มด้วยยูเรียและบ่มด้วยเอนไซม์มีค่า ใกล้เคียงกับน้ำยางขัน ขณะที่จำนวนกรดไขมันระเหยได้และความคงตัวของน้ำยางต่อเครื่องมือ กลนั้นมีค่าต่ำกว่าน้ำยางขัน ทั้งนี้อาจเนื่องจากการที่ปริมาณโปรตีนในน้ำยางลดลงนั่นเอง หลังจากนั้นนำน้ำยางโปรตีนต่ำมาเตรียมเป็นน้ำยางคอมเปาวด์ด้วยสูตรถุงมือยางและทดสอบ พบว่าค่าการทนต่อแรงดึงของยางโปรตีนต่ำคอมเปาวด์มีค่าลดลงเมื่อเทียบกับ ยางขันคอมเปาวด์แต่ค่าการยืด ณ จุดขาดนั้นใกล้เคียงกันทั้งนี้เนื่องมาจากสูตรในการทำยาง คอมเปาวด์ที่ใช้ยังไม่เหมาะสม -

Abstract

Physical properties of deproteinized natural rubber were investigated in order to apply the DPNR latex as non-allergy rubber thin film products. Removal of proteins from natural rubber was made by incubation of high ammonium natural rubber latex (HA-NR) with urea 0.1 wt%, 1 hour in the presence of surfactant at room temperature (DPNR-urea) compared incubation of HA-NR with proteolytic enzyme 0.04 wt%, 24 hours in the presence of SDS at 38°C (DPNR-enzyme). The nitrogen content of the DPNR-urea was reduced to 0.06 wt% from 0.45 wt% under the test condition. Furthermore, amount of water soluble protein was observed through modified lowry method and it was found that water soluble protein content after incubation HA-NR with urea was reduced to 15 μg/g from 42,455 μg/g. The reduction of protein content can be confirmed by observation a chemical structure through FT-IR technique. It is suggesting that the urea treatment is an effective method to remove protein from rubber latex. The physical properties of the DPNR latex were investigated. It was found that %TSC and %DRC of DPNR-urea were similar to that of DPNR-enzyme and HA-NR latex. While VFA number and Mechanical stability of DPNR-urea and DPNR-enzyme was lower than that of HA-NR due to lower amount of protein presence in rubber latex. The mechanical properties were then observed when we applied the DPNR latex to vulcanized rubber glove. Tensile strength of the DPNR decreased compared to that of the commercial HA-NR whereas elongation at break is quite same under the test formulations. This maybe due to rubber compound formulations of deproteinized natural rubber is not suitable.