

## บทคัดย่อ

รหัสโครงการ: MRG4980136

ชื่อโครงการ: การประดิษฐ์แก้วเซรามิกที่ประกอบไปด้วยผลึกเฟอร์โรอิเล็กทริก  
ระดับนาโน

ชื่อนักวิจัย: ผู้ช่วยศาสตราจารย์ ดร. กมลพรรณ เพ็งพัต  
ภาควิชาฟิสิกส์ คณะวิทยาศาสตร์ มหาวิทยาลัยเชียงใหม่ 50200

E-mail Address: kpengpat@gmail.com

ระยะเวลาโครงการ: 2 ปี

คำหลัก: บิสมัทเจอร์มาเนต สมบัติไดอิเล็กทริก แก้วเซรามิก โครงสร้างจุลภาค

ในงานวิจัยนี้ ได้ทำการปลูกผลึกบิสมัทเจอร์มาเนต ( $\text{Bi}_2\text{GeO}_5$ ) ซึ่งเป็นสารเฟอร์โรอิเล็กทริกไร้สารตะกั่วชนิดใหม่ลงในแก้วระบบ  $\text{BiO}_{1.5}\text{-GeO}_2\text{-BO}_{1.5}$  ในอัตราส่วนเท่ากับ  $0.59\text{BiO}_{1.5} : 0.23\text{GeO}_2 : 0.18\text{BO}_{1.5}$  โดยทำการเตรียมด้วยวิธีการหลอมแบบดั้งเดิมใน 2 รูปแบบ คือ วิธีการหลอมโดยใช้ถ้วยอะลูมินา และวิธีการหลอมโดยใช้ถ้วยแพลทินัม ตามลำดับ จากนั้นจึงนำแก้วที่ได้ไปทำการวิเคราะห์ทางความร้อนด้วยเทคนิค DTA เพื่อหาเงื่อนไขที่เหมาะสมในการปลูกผลึก  $\text{Bi}_2\text{GeO}_5$  จากผลการตรวจสอบ พบว่า อุณหภูมิที่เหมาะสมต่อการตกผลึกของแก้วที่หลอมด้วยถ้วยอะลูมินาและแพลทินัม คือ  $545^\circ\text{C}$  และ  $475^\circ\text{C}$  ตามลำดับ จากนั้นจึงนำชิ้นงานที่ผ่านการตกผลึกที่อุณหภูมิดังกล่าวไปทำการวิเคราะห์เฟสองค์ประกอบที่เกิดขึ้นด้วยเทคนิค XRD และตรวจสอบสมบัติทางกายภาพ สมบัติทางไฟฟ้า ตลอดจนโครงสร้างจุลภาค ตามลำดับ จากการทดลอง พบว่า แก้วเซรามิก  $\text{Bi}_2\text{GeO}_5$  ที่เตรียมได้จากการหลอมด้วยถ้วยหลอมแพลทินัมมีสมบัติทางไฟฟ้าที่สูงกว่าแก้วเซรามิกที่เตรียมด้วยถ้วยหลอมอะลูมินา โดยมีค่าคงที่ไดอิเล็กทริก ค่าการสูญเสียไดอิเล็กทริก และค่าสภาพนำไฟฟ้าเท่ากับ 73.9914 0.0063 และ 0.0698 S/m ตามลำดับ

### Abstract

Project Code: MRG4980136

Project Title: The fabrication of glass ceramics consisting of ferroelectric nanocrystals

Investigator : Asst. Prof. Dr. Kamonpan Pengpat  
Department of Physics, Faculty of Science, Chiang Mai University

E-mail Address: kpengpat@gmail.com

Project Period: 2 ปี

Keywords:  $\text{Bi}_2\text{GeO}_5$ ; Dielectric properties; Glass-ceramics; Microstructure

In this research, the fabrication of glass ceramics containing lead free  $\text{Bi}_2\text{GeO}_5$  crystals has been carried out. The  $\text{Bi}_2\text{GeO}_5$  crystals, having orthorhombic structures were precipitated in the  $\text{BiO}_{1.5}$ - $\text{GeO}_2$ - $\text{BO}_{1.5}$  glass system. The study is focusing on the region of 59 mol%  $\text{BiO}_{1.5}$  : 23 mol%  $\text{GeO}_2$  : 18 mol%  $\text{BO}_{1.5}$ . The glasses were prepared by conventional melt-quenching method. The composition of glasses was melted separately in an  $\text{Al}_2\text{O}_3$  and Pt crucible in an air atmosphere. The resulting glasses were analyzed by using Differential thermal analysis (DTA) for determining the crystallization temperature ( $T_x$ ). After that, the glasses were heat treated at their  $T_x$ (s). The as-received glass ceramics from both  $\text{Al}_2\text{O}_3$  and Pt crucibles were investigated in terms of phase composition by X-ray diffraction (XRD). Physical properties, electrical properties and their morphologies of the  $\text{Bi}_2\text{GeO}_5$  glass ceramics from different crucibles were also carried out. It was found that  $\text{Bi}_2\text{GeO}_5$  glass ceramics melted from Pt crucible have better electrical properties than that of the  $\text{Bi}_2\text{GeO}_5$  glass ceramics melted from  $\text{Al}_2\text{O}_3$  crucible. Dielectric constant, dielectric loss and conductivity values of the optimum glass ceramics were 73.9914, 0.0063 and 0.0698 S/m, respectively.