

## บทคัดย่อ

เศษย่างพื้นรองเท้าเป็นขยะย่างชนิดหนึ่งที่เหลือจากการผลิตรองเท้าและยางเป็นจำนวนมาก ซึ่งเป็นสาเหตุที่ก่อให้เกิดปัญหาสิ่งแวดล้อมขึ้น ดังนั้นในงานวิจัยนี้มีวัตถุประสงค์ในการเพิ่มมูลค่า และช่วยลดปริมาณขยะยางลง โดยได้ทำการเตรียมเทอร์โมพลาสติกอิลาสโตร์จากเศษย่างพื้นรองเท้า ที่ผ่านการดีวัลค่าในซ์ และพอลิเอทิลีนชนิดความหนาแน่นต่ำที่อัตราส่วนต่างๆ โดยการนำเศษย่างพื้นรองเท้ามาผ่านการดีวัลค่าในซ์ด้วยไมโครเวฟที่กำลังไมโครเวฟ 90 180 270 360 และ 450 วัตต์ ที่เวลา 30 60 และ 90 วินาที และใช้เตตระเมทิลไथูแรมไดชัลไฟฟ์เป็นสารรีเคลม จากนั้นทำการวิเคราะห์ระดับการ เชื่อมขวางของยางที่ผ่านการดีวัลค่าในซ์จากค่าสัดส่วนเจลและอัตราส่วนการบรวมตัวเป็นฟังก์ชันกับกำลัง ไมโครเวฟที่เวลาต่างๆ กัน เพื่อหาภาวะที่เหมาะสมในการดีวัลค่าในซ์เศษย่างพื้นรองเท้า นอกจากนี้ยัง ทำการศึกษาผลของพลังงานคลื่นไมโครเวฟและสารรีเคลมที่มีต่อสมบัติเชิงกล สมบัติทางกายภาพ สมบัติ ทางความร้อน และสัณฐานวิทยาของเทอร์โมพลาสติกอิลาสโตร์ที่เตรียมได้ ผลการศึกษาพบว่าภาวะที่ เหมาะสมที่สุดในการดีวัลค่าในซ์เศษย่างคือที่กำลังไมโครเวฟ 360 วัตต์ เป็นเวลา 60 วินาที ค่าสัดส่วนเจล และอัตราส่วนการบรวมตัวของยางที่ผ่านการดีวัลค่าในซ์ลดลงเมื่อกำลังไมโครเวฟเพิ่มขึ้นสมบัติเชิงกลและ สมบัติทางกายภาพของเทอร์โมพลาสติกอิลาสโตร์ที่เตรียมได้เพิ่มขึ้นเมื่อปริมาณพอลิเอทิลีนชนิดความ หนาแน่นต่ำเพิ่มขึ้น ในทางตรงข้ามสมบัติเชิงกลและสมบัติทางกายภาพลดลงเมื่อใช้เศษย่างพื้นรองเท้าที่ ผ่านการดีวัลค่าในซ์ด้วยพลังงานไมโครเวฟร่วมกับการใช้สารรีเคลมมาผสานกับพอลิเอทิลีนชนิดความ หนาแน่นต่ำ โดยอัตราส่วนของเศษย่างพื้นรองเท้าและพอลิเอทิลีนชนิดความหนาแน่นต่ำที่เหมาะสมใน การนำไปใช้งานคืออัตราส่วน 80:20 ในภาวะที่เศษย่างพื้นรองเท้าไม่ผ่านการดีวัลค่าในซ์ด้วยไมโครเวฟ และมีการใช้เตตระเมทิลไथูแรมไดชัลไฟฟ์ 2.75 phr และเมื่อทำการเบริ่ยบเทียบกับเทอร์โมพลาสติกอิลาส โตร์ในทางการค้า (Santoprene® 101-87) แล้วพบว่าความทนต่อการฉีกขาดของเทอร์โมพลาสติกอิ ลาสโตร์ที่เตรียมได้นั้นมีค่าที่สูงกว่าเทอร์โมพลาสติกอิลาสโตร์ในทางการค้าในขณะที่ค่าความแข็ง และความทนแรงดึงดันมีค่าที่ใกล้เคียงกัน อย่างไรก็ตามค่าการยึดดึง ณ จุดขาด และความทนต่อการขัดถู นั้นยังมีค่าที่ด้อยกว่าเทอร์โมพลาสติกอิลาสโตร์ในทางการค้า

## Abstract

Shoe sole scrap is a by-product from rubber shoe factory, which can cause an environmental problem. Therefore, the goal of this research was to reduce the amount and increase added values of rubber wastes by preparing thermoplastic elastomers (TPE) from devulcanized shoe sole scrap and low density polyethylene (LDPE) at various ratios. Shoe sole scrap was devulcanized by microwave energy at various microwave power and devulcanizing time (90, 180, 270, 360, and 450 watt and 30, 60, and 90 sec, respectively) and by using tetra methyl thiuram disulfide (TMTD) as a reclaiming agent. The degree of crosslinking was evaluated by measurement of the gel fraction and swelling ratio of devulcanized shoe sole scrap as a function of microwave power and time to identify the optimum condition for devulcanizing shoe sole scrap. The effects of microwave energy and reclaiming agent on the mechanical, physical, and thermal properties as well as the morphology of the TPEs were studied. The results showed that the optimized condition to devulcanize shoe sole scrap by microwave energy was at 360 watt for 60 sec. The gel fraction and swelling ratio of devulcanized shoe sole scrap decreased with increasing microwave power. The mechanical and physical properties of TPEs were increased with increasing LDPE content. In contrast, the mechanical and physical properties of TPEs decreased when the microwave devulcanized shoe sole scrap and reclaiming agent were both added with the LDPE. The suitable ratio for preparing the TPE from this research was 80:20 for non-microwave devulcanized shoe sole scrap and LDPE, with the addition of 2.75 phr of TMTD. The selected TPE formula was compared with commercial TPE (Santoprene® 101-87). The results showed that the tear strength of the prepared TPE was higher than that of the commercial TPE; whereas the hardness and tensile strength values were comparable with those of the commercial one. Nevertheless, it was found that the elongation at break and abrasion resistance of the prepared TPE were still lower than those of the commercial TPE.