

บทคัดย่อ

งานวิจัยนี้ศึกษาการดัดแปรผงแกรไฟต์ที่เหลือจากอุตสาหกรรมหลอมโลหะ เพื่อใช้เป็นสารตัวเติมใน คอมพอสิตยางธรรมชาติ ผ่านปฏิกิริยาออกซิเดชัน (วิธีการ Hummer) และรีดักชันของกรดแอสคอร์บิก ผงแกรไฟต์ที่ได้ถูกวิเคราะห์โดยเทคนิคการวิเคราะห์ธาตุ CHN การเลี้ยวเบนรังสีเอกซ์ *ฟูเรียร์ทรานส์ฟอร์ม อินฟราเรด* สเปกโตรโฟโตมิเตอร์ สเปกโตรสโคปีของอนุภาคอิเล็กทรอนิกส์ที่ถูกปลดปล่อยด้วยรังสีเอกซ์ พื้นที่ผิวจำเพาะของ BET กล้องจุลทรรศน์อิเล็กตรอนแบบส่องผ่าน และ four-point probe พบว่าผงแกรไฟต์ที่มีปริมาณออกซิเจนลดลง แผ่นแกรไฟต์มีความเป็น single layer sheet มากขึ้น ส่งผลให้ค่าการนำไฟฟ้าเพิ่มขึ้นประมาณ 1.96 เท่าเมื่อเปรียบเทียบกับผงแกรไฟต์ก่อนการดัดแปร สมบัติการนำไฟฟ้าของคอมพอสิตยางธรรมชาติพบว่าคอมพอสิตยางธรรมชาติผสมกับผงแกรไฟต์แสดงสัดส่วนวิกฤตที่ 5 phr ให้ค่าการนำไฟฟ้าเท่ากับ 9.06×10^{-6} S/cm ซึ่งใกล้เคียงกับการใช้คาร์บอนแบล็กเกรดนำไฟฟ้าเป็นสารตัวเติม (5 phr, 8.15×10^{-6} S/cm) และสามารถนำไฟฟ้าได้ดีกว่าการใช้คาร์บอนแบล็กเกรด N339 (25 phr, 2.35×10^{-7} S/cm) นอกจากนี้สมบัติเชิงกลของคอมพอสิตยางธรรมชาติผสมร่วมกับผงแกรไฟต์มีค่าใกล้เคียงกับการใช้คาร์บอนแบล็กเกรดนำไฟฟ้าและคาร์บอนแบล็กเกรด N339 เป็นสารตัวเติม

คำสำคัญ: ยางธรรมชาติ, พอลิเมอร์นำไฟฟ้า, แกรไฟต์, แกรไฟน์

ABSTRACT

In this study, the modified graphite waste from metals smelting industry was studied in order to use as an additive in natural rubber (NR) composite via oxidation (Hummers method) and reduction of L-ascorbic acid. The obtained graphene was then characterized by CHN analysis, x-ray diffractometer, fourier transform infrared spectrophotometer, x-ray photoelectron spectroscopy, BET surface area, transmission electron microscopy and four-point probe. The amount of oxygen on the graphene surface was decreased and the graphene sheets became more single layer sheets, resulting in the increase of conductivity (~1.96-fold) compared to graphite (before modification). The electrical conductivity of NR composites with graphene showed the critical concentration at 5 phr (9.06×10^{-6} S/cm) which was comparable with that of NR composite with carbon black Printex XE 2B (5phr, 8.15×10^{-6} S/cm) and was higher than that of NR composite with carbon black N339 (25 phr, 2.35×10^{-5} S/cm). In addition, the mechanical properties of NR composites with graphene were similar to those of NR composite with carbon black Printex XE 2B and carbon black N339.

Keyword: *natural rubber, conducting polymer, graphite, graphene*