

บทคัดย่อ

รหัสโครงการ: RSA5280034

ชื่อโครงการ: การลดความเสียหายเนื่องจากแผ่นดินไหว

ชื่อนักวิจัย: อมร พิมานมาศ

ภาควิชาวิศวกรรมและเทคโนโลยีโยธา สถาบันเทคโนโลยีพระจอมเกล้าเจ้าคุณทหารลาดกระบัง
มหาวิทยาลัยธรรมศาสตร์

Email Address: amorn@siit.tu.ac.th

ระยะเวลาโครงการ: 13 มีนาคม 2552 – 6 ตุลาคม 2555

งานวิจัยนี้เป็นการศึกษาการลดความเสียหายเนื่องจากแผ่นดินไหวของโครงสร้างคอนกรีตเสริมเหล็ก โดยการเสริมกำลังให้โครงสร้างที่มีอยู่เดิมให้มีความต้านทานแผ่นดินไหวหรือความเหนียวขององค์อาคารเพิ่มขึ้น โดยแบ่งเป็น 3 หัวข้อที่ศึกษาได้แก่ 1) การเสริมกำลังการทาบทอเหล็กเสริมในองค์อาคารคอนกรีตเสริมเหล็กด้วยแผ่นเส้นใยโพลิเมอร์ 2) การเสริมกำลังคานคอนกรีตเสริมเหล็กต้านทานแรงเฉือนด้วยเฟอร์โรซีเมนต์ และ 3) การทดสอบและแบบจำลองการเสริมกำลังการทาบทอเหล็กเสริมด้วยเฟอร์โรซีเมนต์

การเสริมกำลังการทาบทอเหล็กเสริมในองค์อาคารคอนกรีตเสริมเหล็กด้วยแผ่นเส้นใยโพลิเมอร์ จะทำการทดสอบตัวอย่างคานจำนวน 8 ตัวอย่าง ประกอบด้วย 1 ตัวอย่างที่ไม่ทาบทอเหล็กเสริม และ 7 ตัวอย่างที่ทาบทอเหล็กเสริม โดยตัวอย่างที่ทาบทอเหล็กเสริม แบ่งเป็น 2 กลุ่มคือ กลุ่ม 15db ที่มีความยาวระยะทาบทอ 200 มม. และกลุ่ม 20db ที่มีความยาวระยะทาบทอ 250 มม. คานทดสอบพิจารณาเป็นคานช่วงเดียว มีความยาวช่วง (Span length) 2.34 ม. ขนาดหน้าตัดกว้าง 15 ซม. ลึก 30 ซม. ทดสอบภายใต้แรงกระทำเชิงสถิต ณ ตำแหน่งกึ่งกลางคานโดยการทดสอบได้พิจารณากำลังรับน้ำหนัก ระยะแอ่นตัว กำลังยึดเหนี่ยวที่บริเวณการทาบทอเหล็กเสริม และกำลังรับน้ำหนักของเหล็กเสริมรับแรงดึง ตัวแปรที่ส่งผลต่อกำลังของเหล็กเสริมบริเวณทาบทอประกอบด้วยความยาวของการทาบทอเหล็กเสริม ระยะหุ้มคอนกรีตและจำนวนรอบของการพันด้วยแผ่นเส้นใยโพลิเมอร์ จากผลการทดสอบพบว่า องค์อาคารที่มีระยะทาบทอเหล็กเสริมที่ไม่เพียงพอหรือสั้นจนเกินไป จะส่งผลให้กำลังรับน้ำหนักและความเหนียวขององค์อาคารลดลง รวมทั้งก่อให้เกิดการวิบัติแบบเปราะซึ่งเกิดจากรอยแตกกว้างปริแตกตามแนวรอยทาบทอเหล็ก การพันด้วยแผ่นโพลิเมอร์เสริมเส้นใยในบริเวณการทาบทอเหล็กเสริมจะส่งผลให้เหล็กเสริมสามารถพัฒนากำลังรับแรงดึงถึงจุดครากได้โดยไม่เกิดการวิบัติแบบปริแตก โดยผลการทดสอบในการวิจัยนี้ได้นำมาใช้พัฒนาแบบจำลองทางคณิตศาสตร์ Tri uniform bond stress model เพื่อคำนวณผลของการโอברัดที่เกิดจากการใช้แผ่นโพลิเมอร์เสริมเส้นใยหุ้มบริเวณการทาบทอเหล็กเสริม รวมทั้งสามารถหาปริมาณของจำนวนแผ่นโพลิเมอร์เสริมเส้นใยที่ต้องการสำหรับเสริมกำลังให้เพียงพอในการต้านทานแผ่นดินไหวได้อีกด้วย

การเสริมกำลังคานคอนกรีตเสริมเหล็กต้านทานแรงเฉือนด้วยเฟอร์โรซีเมนต์จะทำการทดสอบตัวอย่างคานจำนวน 9 ตัวอย่าง ประกอบด้วยคานที่ไม่เสริมกำลัง (คานควบคุม) 3 ตัวอย่าง

และคานที่เสริมกำลัง 6 ตัวอย่าง โดยแปรผันรูปแบบของการเสริมแรง คานทดสอบพิจารณาเป็นคาน simple beam ที่มีความยาวช่วง 2.20 ม. ขนาดหน้าตัดกว้าง 20 ซม. ลึก 40 ซม. ทดสอบภายใต้แรงกระทำเชิงสถิต ณ ตำแหน่งกึ่งกลางคาน รูปแบบการเสริมกำลังด้วยเฟอร์ไรต์เมนต์เพื่อต้านทานแรงเฉือนได้ประยุกต์ใช้โครงเหล็กหุ้มตาข่ายและเหล็กเดือยที่ทำจากเหล็กเส้นกลมดัดเป็นรูปตัวซียึดทางด้านข้างของคานจัดเรียงระยะห่างของเหล็กเดือยที่แตกต่างกัน การทดสอบได้พิจารณาลักษณะการวิบัติของตัวอย่างและประสิทธิผลของการเสริมกำลัง ผลการทดสอบพบว่า คานที่ได้รับการเสริมกำลังต้านทานแรงเฉือนด้วยเฟอร์ไรต์เมนต์สามารถเพิ่มกำลังต้านทานแรงเฉือนได้เป็นอย่างดี โดยเพิ่มกำลังทั้งรับแรงเฉือนและความเหนียว ซึ่งกำลังที่เพิ่มขึ้นจะขึ้นอยู่กับจำนวนและระยะห่างของเหล็กเดือยที่เสริมข้างคาน รูปแบบและวิธีการเสริมกำลัง และเมื่อจำลองในโปรแกรมเพื่อศึกษารอยแตกที่เกิดขึ้นโดยระเบียบวิธีทางไฟไนต์อีลิเมนต์แล้วพบว่ารอยแตกที่ได้มีรูปแบบที่ใกล้เคียงกันกับรอยแตกจากตัวอย่างทดสอบ

การทดสอบและแบบจำลองการเสริมกำลังการทาบทอเหล็กเสริมด้วยเฟอร์ไรต์เมนต์ โดยทำการทดสอบตัวอย่างคานจำนวน 9 ตัวอย่าง ประกอบด้วยคานที่ไม่ทำการทาบทอเหล็กเสริม (คานควบคุม) 1 ตัวอย่าง และคานที่ทำการเสริมกำลัง 8 ตัวอย่าง โดยแบ่งเป็น 2 กลุ่มคือ กลุ่ม 20db ที่มีความยาวระยะทาบท 250 มม. และกลุ่ม 25db ที่มีความยาวระยะทาบท 300 มม. คานทดสอบพิจารณาเป็นคานช่วงเดียว มีความยาวช่วง (Span length) 2.34 ม. ขนาดหน้าตัดกว้าง 15 ซม. ลึก 30 ซม. การเสริมกำลังจะประยุกต์ใช้เฟอร์ไรต์เมนต์ที่ประกอบด้วยมอร์ตาร์และลวดตะแกรงจำนวน 2 ชั้น นอกจากนั้นจะมีการประยุกต์ใช้เหล็กโครงเพื่อที่ทำจากเหล็กเส้นกลม 9 มม. ดัดเป็นรูปตัวซีโอบรัดตัวอย่างคานมีระยะเรียงที่แตกต่างกันออกไป ตัวอย่างคานจะถูกทดสอบภายใต้แรงกระทำเชิงสถิต ณ ตำแหน่งกึ่งกลางคาน โดยการทดสอบได้พิจารณากำลังรับน้ำหนัก ระยะแอ่นตัว กำลังยึดเหนียวที่บริเวณการทาบทอเหล็กเสริม และกำลังรับน้ำหนักของเหล็กเสริมรับแรงดึง ตัวแปรที่ส่งผลต่อกำลังของเหล็กเสริมบริเวณทาบทอประกอบด้วย ความยาวของการทาบทอเหล็กเสริมและรูปแบบการเสริมกำลัง จากผลการทดสอบพบว่า การทาบทอเหล็กเสริมที่มีระยะน้อยกว่า 25 เท่าของเส้นผ่านศูนย์กลางจะไม่สามารถพัฒนากำลังของเหล็กเสริมไปถึงจุดครากได้ การวิบัติจะปรากฏให้เห็นรอยแตกร้าวเกิดขึ้นตามแนวการทาบทอเหล็กเสริมส่งผลให้องค์อาคารคอนกรีตเสริมเหล็กเกิดการวิบัติอย่างฉับพลัน การเสริมกำลังด้วยเฟอร์ไรต์เมนต์ร่วมกับเหล็กโครงสามารถเพิ่มกำลังรับน้ำหนักบรรทุกได้สูงสุดกว่า 100 เปอร์เซ็นต์เมื่อเทียบกับตัวอย่างที่ไม่ได้เสริมกำลังในระยะทาบทเดียวกัน พฤติกรรมของโครงสามารถเปลี่ยนแปลงจากพฤติกรรมที่ไม่มีความเหนียวให้มีความเหนียวได้ จากผลการทดสอบได้นำมาสร้างแบบจำลองโดยอาศัยแบบจำลอง Tri uniform bond stress model เพื่อคำนวณกำลังของเหล็กเสริมหลังจากเสริมกำลังด้วยเฟอร์ไรต์เมนต์ ผลจากการคำนวณแสดงให้เห็นว่ากำลังของเหล็กเสริมที่ได้จากการวิเคราะห์แบบจำลองมีค่าใกล้เคียงกับผลการทดสอบ

Abstract

Project Code: RSA5280034

Project Title: Use of ferrocement to strengthen reinforced concrete members not designed for earthquake

Researcher: Associate Professor Dr. Amorn Pimanmas
School of Civil Engineering and Technology, Sirindhorn International Institute of Technology, Thammasat University

Email Address: amorn@siit.tu.ac.th

Project Duration: March 2009 – September 2012

This research is a study to reduce the damages to reinforced concrete structures due to earthquakes, by strengthening existing structures so that they have increased seismic strength and ductility. The scope of study consists of 1) strengthening of lap splice of reinforcing bars by fiber reinforced polymer sheets, 2) shear strengthening of reinforced concrete members by ferrocement and 3) test and development of mathematical model to predict the strength of lap splice confined by ferrocement

The study on strengthening lap splice by fiber reinforced polymer sheets consists of 8 specimens. One specimen is the control specimen without lap splice and the other 7 specimens are specimens with lap splices. The later 7 specimens are grouped into 2 series, 15db series with lap length of 200 mm and 20db series with lap length of 250 mm. The specimens are tested as simple beam with the span length 2.34 m. The cross section is 15 cm wide and 30 cm deep. The load is monotonically applied at the middle of the beam. The applied load, deflection and lap splice bond strength are measured in the test.

From the experimental results, it is found that the variables that affect the strength of lap splice are splice length, concrete cover and number of FRP layers. The experiment clearly indicated that members with short lap splice length have lower strength and ductility. The failure of the specimens is characterized by brittle splitting crack along lap splice length. The confinement provided by CFRP around lap splice is effective to suppress the splitting crack propagation and enable the steel to develop yield capacity.

Based on the experimental results, the tri-uniform bond stress model has been developed to predict the confinement effect provided by CFRP. The model can also be applied to calculate the required amount of CFRP for strengthening short lap splice region.

The second research project is the shear strengthening of reinforced concrete members by ferrocement jacket. The experiment consists of 9 specimens. Three specimens are the control (unstrengthened) specimen and the remaining 6 specimens are strengthened specimens. The specimen is a beam type with the span length of 2.20 m. The cross section is 20 cm wide and 40 cm deep. The specimen is tested under monotonically applied control displacement at the middle of the span. The ferrocement for shear strengthening has also included the skeleton dowel steel fabricated in a C-shape and is fixed on the side face of the specimens at predetermined intervals. Experimental results have shown that strengthening of specimens by ferrocement can significantly increase shear strength of specimens. The ductility is also enhanced. The increase in shear strength varies with the spacing of skeleton dowel steels and the form of strengthening. Finite element analysis has been conducted to predict the behavior of specimens in the test. It is found that FEM analysis can satisfactorily reproduce cracks, load-deflection response and failure mode.

The third research project involves the test and development of model to predict the lap splice strengthened by ferrocement. In the experiment, 9 specimens have been tested. Among all specimens, one is the control specimen without lap splice. The remaining 8 specimens have short lap splice and are strengthened by ferrocement. The specimens can be grouped into 2 series; 20db series with lap length of 250 mm. and 25db series with lap length of 300 mm. The specimen is a beam type with span length of 2.34 m. The cross section is 15 cm wide and 30 cm high. The ferrocement consists of high strength mortar reinforced by 2 layers of hexagonal wire mesh. Skeleton steel made of 9 mm round bar bent in a C shape is also wrapped around the lap splice to increase the confinement. The load is statically applied to the specimen at the midspan. The applied load, deflection and bond strength of lap spliced bars are measured in the test. From experimental results, it is found that the variable that affects the development of lap splice strength is length of lap splice, form of strengthening and concrete cover. It is also found that if the splice length is less than 25 times bar diameter, the spliced bars cannot develop yield strength. The failure is characterized by a large splitting crack along the lap splice. Strengthening by ferrocement and skeleton steel can increase the load by more than 100%. The failure mode can be changed from brittle splitting failure to ductile flexural mode. Based on experimental results, tri uniform bond stress model is also developed to predict the behavior of specimens confined by ferrocement. Good agreement between model prediction and experimental results can be obtained.