

Abstract

Project code : RSA5880035

Project Title : Fabricating $\text{CsSnI}_{3-x}\text{A}_x$ ($\text{A}=\text{F}$, Cl and Br) p-type thin films for solid state dye-sensitized solar cell applications

Investigator : Assoc. Prof. Dr. Samuk Pimanpang, Department of Physics, Faculty of Science, Srinakharinwirot University

Email : samuk@g.swu.ac.th

Project Period : 3 years and 6 months

In this work, we had studied many materials (MWCNTs, $\text{WS}_2\text{-WO}_x$, $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ and Pt) using as the liquid dye-sensitized solar cell (DSSC) catalysts. WS_2 and $\text{W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$ ($\text{WS}_2\text{-W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$) powders were synthesized using a hydrothermal reaction of micro-sized WO_3 particles in a $\text{HCl} + \text{Na}_2\text{S}\cdot 9\text{H}_2\text{O}$ solution. The resulting $\text{WS}_2\text{-W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$ counter electrode produces an efficiency of 3.37%. To enhance the DSSC's performance, multi-walled carbon nanotubes (MWCNTs) was added to the aforementioned hydrothermal reaction producing $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ composite, which can enhance an efficiency of up to 7.44%, comparable to that of Pt DSSCs (7.53%). This outstanding performance of the $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ based DSSCs is attributed to high electrocatalytic activity and low charge-transfer resistance at the counter electrode and electrolyte interface at the $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ electrode. In case of solid-state dye-sensitized solar cell, $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$ films were prepared from mixed CsI , SnI_2 and/or PbI_2 solutions and used as the hole-transporting layer. The XRD spectra of the as-prepared $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$ films matched the δ -phase (yellow-phase) nonperovskite structure quite well. A $\text{CsSn}_{0.5}\text{Pb}_{0.5}\text{I}_3$ based S-DSSC generated the highest efficiency (3.47%) of the five conditions ($\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$, $x = 0, 0.2, 0.5, 0.8$ and 1). This is attributed to the dark color and good continuity of the $\text{CsSn}_{0.5}\text{Pb}_{0.5}\text{I}_3$ film, its high shunt-resistance ($10,377.10\ \Omega$) and high incident-photon collecting efficiency of $\text{CsSn}_{0.5}\text{Pb}_{0.5}\text{I}_3$ based S-DSSCs. In case of the perovskite solar cell, $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$ perovskite were fabricated and used as the light absorber in the hole-transporting-layer free perovskite solar cell. The highest efficiency of 3.95% was gained from the $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$ perovskite solar cells. There are still many factors (TiO_2 or perovskite solar thickness) have to be optimized for the better perovskite solar cell performance.

Keywords: dye-sensitized solar cell, perovskite solar cell, $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$, $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$

บทคัดย่อ

รหัสโครงการ : RSA5880035

ชื่อโครงการ : การสังเคราะห์สาร $\text{CsSn}_{1-x}\text{A}_x$ ($\text{A}=\text{F}$, Cl and Br) แบบ p-type สำหรับใช้เซลล์แสงอาทิตย์ชนิดสีย้อมไวแสงแบบแข็ง

ชื่อนักวิจัย : รองศาสตราจารย์ สมักร์ พิมานแพง ภาควิชาฟิสิกส์ คณะวิทยาศาสตร์ มหาวิทยาลัยศรีนครินทรวิโรฒ

E-mail Address : samuk@g.swu.ac.th

ระยะเวลาโครงการ : 3 ปี และ 6 เดือน

ในโครงการวิจัยนี้กลุ่มผู้วิจัยได้ศึกษาวัสดุหลายชนิด คือ MWCNTs, $\text{WS}_2\text{-WO}_x$, $\text{WS}_2\text{-W}_5\text{O}_{14}$ -MWCNTs และ Pt สำหรับนำมาใช้เป็นสารคาร์ตาไลต์ในระบบเซลล์แสงอาทิตย์ชนิดสีย้อมไวแสงแบบของเหลว (liquid dye-sensitized solar cell) ซึ่งอนุภาค WS_2 และ $\text{W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$ ($\text{WS}_2\text{-W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$) เตรียมด้วยกระบวนการไฮโดรเทอมอลล์อนุภาคไมโคร WO_3 ในสารละลาย HCl ผสม $\text{Na}_2\text{S}\cdot 9\cdot \text{H}_2\text{O}$ ผลการศึกษาพบว่าฟิล์ม $\text{WS}_2\text{-W}_{18}\text{O}_{49}/\text{W}_5\text{O}_{14}$ ให้ค่าประสิทธิภาพ 3.37% เมื่อผสม MWCNTs ลงในกระบวนการไฮโดรเทอมอลล์สามารถได้อนุภาคผสม $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ และอนุภาคผสมนี้ให้ค่าประสิทธิภาพเซลล์เป็น 7.44% เพราะว่า $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ มีค่า electrocatalytic activity ที่สูง และค่า charge-transfer resistance ที่ผิวของ $\text{WS}_2\text{-W}_5\text{O}_{14}\text{-MWCNTs}$ ที่ต่ำ สำหรับเซลล์แสงอาทิตย์ชนิดสีย้อมไวแสงแบบสถานะของแข็งได้ใช้ฟิล์ม $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$ ที่เป็นชั้นนำส่งโฮล ผลของการเลี้ยวเบนรังสีเอกซ์ของฟิล์ม $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$ พบว่าตรงกับโครงสร้าง δ -phase nonperovskite โดยฟิล์ม $\text{CsSn}_{0.5}\text{Pb}_{0.5}\text{I}_3$ ให้ค่าประสิทธิภาพสูงเท่ากับ 3.47% ซึ่งสูงกว่าเงื่อนไขอื่นๆ ($\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$, $x = 0, 0.2, 0.5, 0.8$ and 1) การที่ฟิล์ม $\text{CsSn}_{0.5}\text{Pb}_{0.5}\text{I}_3$ มีประสิทธิภาพที่สูงเพราะฟิล์มมีความต่อเนื่องและมีค่า shunt-resistance ($10,377.10 \Omega$) ที่สูง สำหรับเซลล์แสงอาทิตย์แบบเพอร์รอฟสไกต์ ได้ทำการเตรียมฟิล์มเพอร์รอฟสไกต์ $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$ เป็นสารดูดกลืนแสงในระบบเซลล์แสงอาทิตย์เพอร์รอฟสไกต์แบบไม่มีชั้นนำส่งโฮล ผลการศึกษาพบว่าฟิล์มเพอร์รอฟสไกต์ $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$ สามารถใช้เป็นตัวดูดกลืนแสง และได้ค่าประสิทธิภาพสูงสุดเท่ากับ 3.95% สำหรับในงานเซลล์แสงอาทิตย์เพอร์รอฟสไกต์นี้เราจะพยายามหาเงื่อนไข เช่น ความหนาของฟิล์ม TiO_2 และความหนาของฟิล์ม $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$ เพื่อให้ได้ค่าประสิทธิภาพที่ดีขึ้น และเขียนเป็นเปเปอร์ต่อไป

คำหลัก: เซลล์แสงอาทิตย์ชนิดสีย้อมไว, เซลล์แสงอาทิตย์เพอร์รอฟสไกต์, $\text{CsSn}_{1-x}\text{Pb}_x\text{I}_3$, $\text{CH}_3\text{NH}_3\text{Pb}(\text{SCN})_2\text{I}$